

Test Report No. : Q00235890a 001f
Page 4 of 6
2. Volatile Organic Substances

Test method: The test was performed according to the 61th Communication on testing of plastics, Bundesgesundheitsbl. 46 (2003) 362.

Limit: Recommendation of Plastics Intended to Come into Contact with Food in BfR, "Kunststoffempfehlungen" part XV, 2007, silicone.

The following test condition was stipulated : 200°C for 4 hours

Test No:	T001		Limit
Material No:	M001		
Parameter	Unit	Result	
Volatile organic substances	%	0.39	0.5

Abbreviation: % = percentage


Remark:

*1 The examined item meets the requirement.

Test Report No. : Q00235890a 001f

Page 6 of 6

Sample photo:



- END -